

## PENEBAR PRIMER

### DESCRIPTION

Penebar Primer enhances the bonding between preformed sealants and concrete surfaces aiding in the installation process. Stops water penetration of the concrete. Conveniently applied at the job site.

### RECOMMENDED FOR

Penebar Primer should be applied to the substrate by brush prior to installation of Penebar preformed joint sealer.

### DIRECTIONS FOR USE

Carefully brush off all dust and debris and brush apply a coat of Penebar Primer to the area where Penebar preformed joint sealer is to be placed.

### PHYSICAL PROPERTIES

#### Color:

Bright Orange

#### % Solids:

20% minimum

#### Solvent Type:

Water

#### Flash Point:

200°F (93°C) minimum

#### Weight / Gallon:

8.0 lbs (3.6 kg)

#### Dry Time @ 77°F (25°C):

10 minutes

#### Dry Time @ 40°F (4°C):

60 minutes

### Clean Up:

Soap and Water

### Coverage Per Gallon:

Approximately 400 sq ft (37 m<sup>2</sup>) on wet cast concrete. Coverage diminishes on dry cast concrete.

### Appropriate Substrates:

Concrete, Plastic, Metal

### Min. Storage Temperature:

40°F (4°C) Product should not be allowed to freeze

### Min. Application Temperature:

20°F (-7°C)

### Surface When Dry:

Tacky

### WARRANTY

ICS PENETRON INTERNATIONAL LTD. warrants that the products manufactured by it shall be free from material defects and will conform to formulation standards and contain all components in their proper proportion. Should any of the products be proven defective, the liability to ICS PENETRON INTERNATIONAL LTD. shall be limited to replacement of the material proven to be defective and shall in no case be liable otherwise or for incidental or consequential damages. ICS PENETRON INTERNATIONAL LTD. MAKES NO WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AND THIS WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED. User shall determine the suitability of the product for his intended use and assume all risks and liability in connection therewith.